



Structure ID: RP-01 - Roof Panel 1

P1 **CVT**

ROOF - EASI-SET BUILDING - RP-01 - 121" x 204"

Job Name: 25-3470P9 CCHS Precast Building
Job Location: 5185 Fort Campbell BLVD
Contractor: Christian County Board of Education C/O A&K Construction

Plant: Beaver Dam
9/29/2026 2:19:01 PM


Tech: J. Coppage
PC: E. Bradley



Structure ID: RP-01 - Roof Panel 1

P1 CVT

ROOF - EASI-SET BUILDING - RP-01 - 121" x 204"



Job Name: 25-3470P9 CCHS Precast Building
Job Location: 5185 Fort Campbell BLVD
Contractor: Christian County Board of Education C/O A&K Construction

Plant: Beaver Dam
9/29/2026 2:19:01 PM

Tech: J. Coppage
PC: E. Bradley



Structure ID: RP-01 - Roof Panel 1

P1 CVT

ROOF - EASI-SET BUILDING - RP-01 - 121" x 204"



PT Check for Roof Panels RP-01/RP-02 (PCI MNL)

Material Data

(7) Wire lo-lax Strand - ASTM A416

Φ_{ps} 0.500 in,

A= 0.153 in²

E= 28500000 psi

fpu= 270 ksi

Strand Length 667 in

Assume (Info supplied by strand manufacturer)

k= 0.0007 Wobble Friction Coeff.

μ = 0.05 Curvature friction coeff. (Initial tension of 3,000 lbs)

Strand is to be stressed 70% of ultimate

= 28917 lbs



Cable Configuration

Adjustments to tensioning

1) Dead end anchor wedge seating loss

~ Expected to be 1/8 in

2) Live end anchor wedge seating loss

~ Expected to be 1/8 in, recommend over pull 1/8"

3) Elastic Shortening

Neglect for this pnl

4) Friction Loss

Additional force to overcome frictional forces between strand and sheathing

Tensioning Computations

$$\text{Basic Elongation} = \frac{(\text{Force required beyond initial tension}) (\text{Length of strand between anchorages})}{(\text{Area of strand}) (\text{Modulus of Elasticity})}$$
$$= 3.96 \text{ in}$$

Adjustments

a) Dead end anchor wedge seating: Add 1/8" to elong. No force adjustment req'd

Add 1/8 in

b) Live end seating: over pull by 1/8"

1/8 in

Force adjustment $t = 817 \text{ lbs}$ $\alpha = \text{curvature} = \pi(2.5) = 7.85 \text{ radians}$

$$\text{c) Friction losses } \frac{PD}{PS} = e^{-\left(\frac{kL}{2} + \mu\alpha\right)}$$

$$= 0.649$$

$$\text{Avg. strand force} = 0.825 \quad 17.53\% \text{ Loss}$$

Recommend sequential jacking at both ends of the tendon be used to reduce the overstressing the strand at the live end

Friction loss at mid-point of tendon

$$\frac{PD}{PS} = e^{-\left(\frac{kL}{2} + \mu\alpha\right)}$$

$$= 0.806$$

Avg. strand force over

$$\text{half of tendon} = 0.903 \quad 9.71\% \text{ Loss}$$

Total force and elongation at live end must be increased to compensate for friction losses

Elong. Adjustment = 0.385 in

Force Adjustment = 2806 lbs

Total Force Required = 32541 lbs **OK**

Elongation Summary:

Gross Theoretical Elongation			
Basic Elongation	3.96 in		
Dead End Seating Loss	0.125 in		
Live End Seating Loss	0.125 in		
Friction Losses	0.385 in		
Total Elongation	4.60 in		
Rounded	4 10/16 in		
Tolerance limits	-7.0%	4.28 in	4 4/16 in
	+7.0%	4.92 in	4 15/16 in